

SiSiB[®] PC1441 SILANE

- 1 -

CHEMICAL NAME

Morpholinylmethyltriethoxysilane

Synonym: Triethoxylsilylmethylmorpholine

CHEMICAL STRUCTURE

$$\begin{array}{c|c} OC_2H_5 \\ \hline O \\ OC_2H_5 \\ \hline OC_2H_5 \\ \end{array}$$

INTRODUCTION

SiSiB® PC1441 is a bifunctional organosilane possessing a reactive amino group and hydrolyzable inorganic ethoxysilyl groups. The dual nature of its reactivity allows SiSiB® PC1441 to bind chemically to both inorganic materials and organic polymers, thus functioning as an adhesion promoter, surface modifier and as a reactant for product modification.

The close proximity of the nitrogen atom to the silicon atom can accelerate hydrolysis reaction compared to (amino-propyl)silanes.

TYPICAL PHYSICAL PROPERTIES

CAS No.	N/A
EINECS No.	N/A
Formula	C ₁₁ H ₂₅ NO ₄ Si
Molecular Weight	263.41
Boiling Point	266°C [760mmHg]
Flash Point	115°C
Color and Appearance	Clear to straw liquid
Density _{25/25°C}	0.999
Refractive Index	1.444 [25°C]
Purity:	Min.97.0%

Power Chemical
IS09001 IS014001 certificated

Copyright© 2009 Power Chemical Corporation Ltd. SiSiB® is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit www.SiSiB.com or www.PCC.asia



SiSiB[®] PC1441 SILANE

- 2 -

APPLICATIONS

SiSiB® PC1441 can be used as coupling agent, adhesion promoters, surface modifier etc.

SiSiB® PC1441 can be used as starting material in the synthesis of amino-functional silicones.

PACKING AND STORAGE

SiSiB® PC1441 is supplied in 180Kg steel drum or 900Kg IBC container.

In the unopened original container SiSiB® PC1441 has a shelf life of one year in a dry and cool place.

Notes

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: silanes@SiSiB.com.

