




SiSiB[®] PC4100 SILANE

- 1 -

CHEMICAL NAME

Gamma-Methacryloxypropyltrimethoxysilane

CHEMICAL STRUCTURE



INTRODUCTION

SiSiB[®] PC4100 is a methacryl-functional silane; it is a clear, light and heat sensitive liquid with a faintly sweet odour.

SiSiB[®] PC4100 is used as adhesion promoter at organic/inorganic interfaces, as surface modifier (e.g. imparting water repellency, organophilic surface adjustment) or as crosslinking of polymers). It is used as a coupling agent to improve the physical and electrical properties of glass-reinforced and mineral-filled thermosetting resins under exposure to heat and/or moisture. It is typically employed as a blend additive in resin systems that cure via a free radical mechanism (e.g. polyester, acrylic) and in filled or reinforced thermoplastic polymers, including polyolefins and polyurethanes. It is also used to functionalize resins via radical initiated processes - copolymerization or grafting - and to modify surfaces.

APPLICATIONS

SiSiB[®] PC4100 can improve strength as glass fiber size composite in reinforced polyester composites.

SiSiB[®] PC4100 can enhance initial and wet strength of reinforced polyester resin composites.

SiSiB[®] PC4100 can enhance the wet electrical properties of many mineral-filled and reinforced composites.

Power Chemical
ISO9001 ISO14001 certified

Copyright© 2009 Power Chemical Corporation Ltd.
SiSiB[®] is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit www.SiSiB.com or www.PCC.asia



SiSiB® PC4100 SILANE

- 2 -

SiSiB® PC4100 crosslinked acrylic type resins can improve adhesion and durability of adhesives and coatings.

TYPICAL PHYSICAL PROPERTIES

CAS No.	2530-85-0
EINECS No.	219-785-8
Formula	C ₁₀ H ₂₀ O ₅ Si
Molecular Weight	248.35
Viscosity _{25°C}	2 cSt
Boiling Point	255°C [760mmHg]
Flash Point	108°C
Color and Appearance	Colorless transparent liquid
Density _{25/25°C}	1.045
Refractive Index	1.430 [25°C]
Min. Purity	99.0%

Solubility: SiSiB® PC4100 is soluble in methanol, ethanol, isopropanol, acetone, benzene, toluene, and xylene. After hydrolysis, it is soluble in water with adequate stirring if the pH is adjusted to 4.0. Hydrolysis releases methanol.

SiSiB® PC4100 shows copolymerization or grafting reactions when catalyzed by (organic) initiator systems, e.g. peroxides or by radiation (e.g. UV).

PACKING AND STORAGE

SiSiB® PC4100 is supplied in 25Kg plastic drum, 200Kg steel drum or 1000Kg IBC container.

In the unopened original container SiSiB® PC4100 has a shelf life of one year in a dry and cool place.

NOTES

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

Power Chemical
ISO9001 ISO14001 certified

Copyright© 2009 Power Chemical Corporation Ltd.
SiSiB® is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit www.SiSiB.com or www.PCC.asia



SiSiB[®] PC4100 SILANE

- 3 -

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: silanes@SiSiB.com.

Power Chemical
ISO9001 ISO14001 certificated

Copyright© 2009 Power Chemical Corporation Ltd.
SiSiB[®] is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit www.SiSiB.com or www.PCC.asia