

SiSiB[®] HR0660 HCE

- 1 -

INTRODUCTION

SiSiB® HR0660 is heat cured silicone rubber for extrusion.

KEY FEATURES

Excellent extrusion process ability

Well balanced physical properties

ROHS test passed.

TYPICAL PHYSICAL PROPERTIES

Product	SiSiB® HR0660 HCE
Appearance	Translucent
Curing Agent	C-8
Curing Agent Content	2.0%
Curing Condition	170°C×5min
Hardness (Shore A)	60+/-3
Tensile Strength (MPa)	Min. 7.0
Elongation (%)	Min. 300
Tensile Set (%)	Max.10.0
Tear Strength (KN/m)	Min. 16.0

APPLICATIONS

Wire/Cable

Tubes,

Seals, Parts

PACKING AND STORAGE

SiSiB® HR0660 is supplied in 20Kg box, with plastic bag inside.

Power Chemical
IS09001 IS014001 certificated

Copyright© 2008 Power Chemical Corporation Ltd. SiSiB® is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit www.SiSiB.com or www.PCC.asia



SiSiB[®] HR0660 HCE

- 2 -

Store in a cool and dry place out of direct sunlight.

NOTES

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: support@SiSiB.com.

